



**ROLHAS TÉCNICAS 1+1 E AGLOMERADAS
TECHNICAL CORKS 1+1 AND AGGLOERATED CORKS
BOUCHONS TECHNIQUES 1+1 ET AGGLOMERÉES**

Ficha Técnica / Technical Data / Fiche Technique

Especificações/Specifications/Spécifications	Standards 1+1	Standards AGGLO
Diâmetro/Diameter/Diamètre	± 0,3 mm	± 0,3 mm
Comprimento/Length/Longueur	± 1,0 mm	± 0,5 mm
Humidade/Moisture/Humidité	4% - 9%	4% - 9%
Espessura Discos/Disc Thickness/ Épaisseur disques	> 4 mm	-
Ovalidade/Ovality/Ovalisé	<0,3 mm	<0,3 mm
Pó/Cork dust/Poudre	<3 mg	<3 mg
Força Extração/Extraction force/Force d'extraction	20-40 DaN	15-40 DaN
Densidade/Density/Densité	250 - 340 Kg / m3	250 - 340 Kg / m3
Resíduos Peróxido/Peroxide residues/Résidus Peroxyde	<0,2 mg	<0,2 mg
Tempo de Recuperação diametral Diameter recovering time Temps récupération du diamètre	Standards 1+1	Standards AGGLO
Imediato/Immediate/Immédiat	≥ 87%	≥ 86%
1 Hora/Hour/Heure	≥ 93%	≥ 92%
Microbiologia/Microbiology/Microbiologie	Standards 1+1	Standards AGGLO
Leveduras/Moulds/ Levures	≥ 10 Ufc	≥ 10 Ufc
Bactérias/Bactéria/Bactéries	≥ 30 Ufc	≥ 30 Ufc



"Natural is the best..."

www.corsancorks.com